



---

|                            |                          |
|----------------------------|--------------------------|
| <b>Base Material:</b>      | Texturized E-Glass       |
| <b>Weave</b>               | Plain                    |
| <b>Thickness</b>           | 7.1 mil                  |
| <b>Weight</b>              | 6.10 oz/yd <sup>2</sup>  |
| <b>Count</b>               | Warp – 44<br>Fill – 31   |
| <b>Yarn</b>                | ECG 75 1/0 (Warp & Fill) |
| <b>Tensile Strength</b>    | Warp – 350<br>Fill - 270 |
| <b>Roll Length</b>         | 50 yards                 |
| <b>Service Temperature</b> | 1000°F                   |