



Base Yarn:	Fiberglass/E-Glass
Breaking Strength:	20 Lbs.
Yards/Lb.:	Style D-18 = 2155 Style D-24 = 1610
Nominal Diameter/Yard:	Style D-18 = 0.017" Style D-24 = 0.020"
Construction:	EC6 S 340 Z
Turns/Inch:	8.64
Service Temperature:	1000°F
Standard Spool Weight:	2 Lbs.
Percent Teflon:	16%
Mil Spec:	Mil-C-20079 Ty 3 Cl 3